



BITUMAT
بيتومات

The Power to Perform

تقوية في الأداء



NRC A MEMBER



Follow us:



BITUMAT BITUSEAL 1500 CLX - MR

DESCRIPTION

BITUSEAL 1500 CLX – MR is a self-adhesive, extremely flexible waterproofing membrane. The elastic self-adhesive, SBS Modified bitumen compound is reinforced with rotproof 50 – 60 GSM Glassfiber matt backed with a Cross Laminated HDPE Film resulting in outstanding physical properties making Bituseal 1500 CLX - MR as one of the most rugged self-adhesive membranes. The advanced carrier film is manufactured by cross laminating and chemically bonding the layer together.

USES

BITUSEAL 1500 CLX – MR is ideal for damp completely before the application of the Bitumat proofing, foundations, bridges, viaducts and other Bituseal 1500 CLX - MR. sub-grade applications.

When used with Bitumat water-stops cast into the Bitumat Bituseal 1500 CLX – MR shall be laid by concrete shell, it will provide a high performance, peeling back the protective release paper and chemically resistant and fully continuous applying the adhesive face onto the prepared waterproofing / tanking system for basement and surface. The material should be brushed on to the sub-structures.

OUTSTANDING FEATURES

- coating elongation and is capable of bridging laps and well rolled with a firm pressure using a shrinkage cracks in the concrete. It's high Bitumat Roller to ensure complete adhesion and elongation and self-healing properties enable it continuity between the layers. In cool conditions, to accommodate minor settlement also. the application of the gentle heat between layers
- **The cross lamination** provides dimensional by hot air gun or soft flame will assist promoting stability, high tear strength, puncture and impact adhesion at lap joints. Care to be taken that no resistance to the membrane. wrinkles are formed.
- **Self-adhesive.**
- **Has excellent resistance** to aggressive soils Bitumat Bituseal 1500 CLX – MR to extend about 300mm beyond line or retaining walls to allow continuity with the vertical application. Any punctures or damaged areas should be cleaned and patched using Bitumat Bituseal 1500 CLX – MR with 50 – 100 mm laps all around. Pipe entries maybe sealed prior to the application of Bitumat Bituseal 1500 CLX - MR.
- **Ease of application.**

GENERAL DATA

Nominal Roll Length	:	20m roll
Nominal Roll Width	:	1 mtr.
Nominal Weight	:	32 kg & 42 Kgs
Thickness	:	1.60mm & 2.10 mm

PACKAGING

Palletization 16 rolls per pallet.
Store upright in a dry condition below 40°C.

QUALITY CONTROL

In addition to stringent regular tests by Bitumat protection or Bitumat protection boards spot laboratory, our products are tested periodically by bonded. Vertical faces to be protected if required Third parties.

INSTALLATION TOOLS REQUIRED:

Knife, Measuring tape, Marking string, Gloves etc.

APPLICATION

Measures should be taken to ensure that all surfaces are free from ice, frost or condensation. Installation is recommended between +5°C and +40°C.

All surfaces to receive Bituseal 1500 CLX – MR shall be smooth, regular, dry, free from nails and primed with one coat of Bitumat Primer applied by brush or roller at a rate of 3 - 4 sqm/liter depending on the porosity o the surface, and allowed to dry

Adjacent rolls are aligned and overlapped minimum 50 mm at side laps and 100 mm at end

the application of the gentle heat between layers

Once the application of Bituseal is complete, care has to be taken to ensure proper protection against physical damage. Other tradesmen move around the site and the possibilities of physical damage are increased. It is recommended to apply a minimum 25-50mm screed as horizontal

against damage from backfilling and fixing of reinforcement by using boards recommended by BITUMAT and spot bonded.



BITUMAT
بيتومات

BITUMAT BITUSEAL 1500 CLX - MR

TECHNICAL DATA

MBM16 110-I R-00 100

Property	Typical Value		Test Method
	CLX-MR		
Elongation of Adhesive Compound coating compound (%)	2000		ASTM D 882
Adhesive compound softening point (C)	110		UEAtc, ASTM D 36
Top Surfacing			
Tensile Strength	Longitudinal	² 35 (N/mm)	ASTM D 882
	Transverse	² 30 (N/mm)	
Elongation	Longitudinal	550 %	ASTM D 882
	Transverse	600 %	ASTM D 882
Tear Strength	Longitudinal	180 N/mm	ASTM D 1004
	Transverse	190 N/mm	
Nominal Thickness (mm)	1.6 & 2.1		UEAtc, ASTM D 751,
Tensile Strength	Longitudinal	350 N/5cm	ASTM D 5147
	Transverse	250 N/5cm	ASTM D 5147
Tear Strength	Longitudinal	210 N	ASTM D 5147
	Transverse	130 N	
Puncture Resistance	210 N		ASTM E 154
Resistance to Hydrostatic Pressure	7 bar		DIN 1048, ASTM D5385
Flexibility at Low Temperature	0 -20 C Pass		UEAtc
Adhesion Strength to Primed Concrete	2.2 N/mm		ASTM D 1000
Adhesion Strength to self	2.2 N/mm		ASTM D 1000
Water Vapour Transmission	² 0.2 gr/m /24hrs		ASTM E 96
Water Absorption	@ 24 hrs.	0.14 %	ASTM D 570
	@ 35 days	0.95 %	
Environmental Resistance	Conforms		ASTM D 543
Crack bridging ability	2 mm		ASTM C 836

Information given in this Technical Data Sheet reflects typical median properties based on laboratory test, and practical experience; subject to the tolerance levels of UEAtc directives. However, as the product is often used under conditions beyond our control, we can't warrant but the product itself.

THIS PUBLICATION AUTOMATICALLY SUPERSEDES ALL PREVIOUS PUBLICATIONS RELATING TO THIS PRODUCT.

BITUMAT COMPANY LIMITED

Corporate Office : P.O. Box 7487, Dammam 31462, Kingdom of Saudi Arabia Tel. No. (966-13) 8121210 / 8121213 Fax No: (966-13) 8121190
Central Region : P.O. Box 58698, Riyadh 11515, Kingdom of Saudi Arabia Tel. No. (966-11) 4770443 / 4792553 Fax No: (966-11) 4762318
Western Region : P.O. Box 12605, Jeddah 21483, Kingdom of Saudi Arabia Tel. No. (966-12) 6644449 Fax No: (966-12) 6640506
Bangladesh : Global Business Solution, Nawabpur Tower Market, Tel: 02 57164405, Mobil: 01916822106

The Power to Perform

قوة في الأداء



NRCA MEMBER



Follow us:

